

**ANALISA AYAK AGREGAT KASAR
(SNI 03-1968-1990/ ASTM C.33)**

Contoh : Batu Pecah (Split)
Tanggal uji :

Ukuran Ayakan (mm)	Tertahan		Kumulatif		SPEK. ASTM	
	Berat (gram)	Prosen (%)	Tertahan (%)	Lolos (%)	C.33	
	I	I			Min.	Maks.
50.00	0.0	0.00	0.00	100.00		
37.50	0.0	0.00	0.00	100.00		
25.00	0.0	0.00	0.00	100.00	100	100
20.00	0.0	0.00	0.00	100.00	90	100
16.00	1227.3	51.51	51.51	48.49	20	55
10.00	1096.4	46.02	97.53	2.47	0	15
4.75	58.8	2.47	100.00	0.00	0	5
2.36	0.0	0.00	100.00	0.00		
1.18	0.0	0.00	100.00	0.00		
0.60	0.0	0.00	100.00	0.00		
0.30	0.0	0.00	100.00	0.00		
0.15	0.0	0.00	100.00	0.00		
0.075	0.0	0.00	100.00	0.00		
<0.075	0.0	0.00	100.00	0.00		
Jumlah	2382.5	100.00	949.05	450.95		
FM			6.98		8.10	7.80

